

**QUASI-ONE-DIMENSIONAL
ELECTRONIC TRANSPORT
PROPERTIES OF
CONDUCTING POLYMER
NANOWIRES**

Thesis submitted for the degree of

DOCTOR OF PHILOSOPHY (SCIENCE)

in

PHYSICS

by

ABHISAKH SARMA

Department of Physics

University of Calcutta

JULY, 2014

To my teachers

Abstract

This thesis reports the study of the Charge Density Wave (CDW) state in polypyrrole (PPy) and composite gold-polypyrrole (AuPPy) nanotubes. Here we have presented the synthesis of the both pure and composite PPy nanotubes and results of electronic transport property studies. A brief description of techniques used for characterization of these nanotubes is given. Details of electronic transport properties of these nanotubes is presented in subsequent chapters. Magneto-transport and hard x-ray photoemission spectroscopy measurement results reveal that the disorder increases but doping reduces in both PPy and AuPPy nanotubes with the decrease of nanotubes-diameter. But due to gold incorporation the disorder as well as doping reduces. The reduction of disorder and doping in the system increases the stability of CDW state in gold-incorporated nanotubes. Low temperature dielectric measurements of PPy nanotubes reveal that the dielectric constant is of the order of 10^3 , which is the usual situation for a CDW state. Relaxation time for the dielectric loss peak $\tau_0(T)$, whose temperature dependence scales with low bias DC conductance, both showing Arrhenius behavior with a gap of around 3.5 meV. These are classic phenomena observed in various conventional CDW materials. We have tuned the CDW state in these PPy nanotubes by incorporating gold nanoparticles and studied its effect using dielectric spectroscopy. We have shown by x-ray scattering technique that the static value of dielectric constant in PPy nanotubes can be tuned to a colossal value by tuning the wt% of gold nanoparticles. Switching transition observed here for both types of nanotubes have been shown to be of metal-insulator type transition using PPy nanotubes by studying magnetoresistance and Zhabrodskii plots.

Acknowledgement

First and foremost, I would like to convey my profound gratitude to my supervisor, Prof. Milan K. Sanyal who made it possible to flourish this thesis work on such an exciting research area of the physics of conducting polymer nanowires. I have been blessed with his proficient guidance, his inspiration and moral boosts especially during the hard times. It was 2007 September when I started working with him. I could realize his enormous effort to remove all the hurdles from our paths so that we could focus on science. Even more, it was from him that I began to pick up the instincts of a successful experimentalist: which avenues to attack first when confronted with a problem, when to abandon the path you're on and try another, and when to keep digging because the path you're on will, eventually, lead to success.

I thank Atikurda, Sirshenduda, Rupakda, Mrinalda, Santanu, Arpan, Arka, Gouranga, Arnab for their help during the lab set up and experiment. I thankful to Dr. Srihari Velega for his lots of help during correction of my thesis.

I owe my parents much of what I have become. They put education as topmost priority in my life, and raised me to set high goals for myself. I dedicate this work to them to honor their love, patience and support during these years.

As well as I specially thanks to my mother Alpana Sarma, my Father Subimal Sarma, my wife Falguni Sarma for their continuous support which made me tension free to carry out my research work. And I thank my son Abhijnan sarma.

Kolkata

Abhisakh

July 25, 2014

Contents

1	Introduction	3
1.1	Quasi 1D: a brief introduction	3
1.1.1	Speciality of 1D electronic systems	5
1.2	Polymer nanowire and quasi-1D	15
1.2.1	Basics	15
1.2.2	Conjugate Polymer	17
1.2.3	Conduction carrier in conducting polymers	20
1.3	Outline of the thesis	24
2	Experimental	27
2.1	Introduction	27
2.2	Synthesis of nanowires	28
2.2.1	Synthesis of gold-polypyrrole composite nanotube in chemical route	29
2.2.2	Polypyrrole nanotube & chemical route	32
2.3	Characterization	32
2.3.1	Scanning Electron Microscopy (SEM)	32
2.3.2	Transmission Electron Microscopy (TEM)	34
2.3.3	Secondary Ion Mass Spectroscopy(SIMS)	38
2.3.4	Magnetron Sputtering	40

2.3.5	Thermal evaporator [Designed in Lab]	41
2.4	Electron beam Lithography	44
2.4.1	Types of e-beam resist	44
2.4.2	Pattern Designing	45
2.4.3	Connecting single polypyrrole nanotube for electronic transport measurements (RECIPE)	46
2.5	Connections of multiple nanotubes	53
2.6	Low Temperature Measurements	54
2.6.1	DC and AC measurement setup	55
2.6.2	Dielectric Measurement	59
2.6.3	Data acquisition	59
2.7	X-ray (Synchrotron) measurement	60
3	Charge density wave state in pure and composite polypyrrole nanotubes	61
3.1	Introduction	61
3.2	Hard X-ray Photoemission Spectroscopy (HAXPES)	62
3.2.1	EXPERIMENTAL	62
3.2.2	RESULTS & DISCUSSIONS	64
3.3	Variation of disorder in polypyrrole and gold incorporated polypyrrole nanotube:	69
3.3.1	Results & Discussions	72
3.4	Charge Density Wave (CDW) like behavior in Polypyrrole and gold-polypyrrole nanocomposite nanotube:	75
3.4.1	Current-Voltage Characteristics (I-V)	76

3.5	Conclusion	90
4	Dielectric properties of CDW state in Gold-incorporated polypyrrole nanotube	93
4.1	Introduction	93
4.2	Dielectric properties of Organic-Metal system:	94
4.3	Dielectric behavior of CDW :	97
4.4	Tuning the dielectric constant of polypyrrole nanotube using gold-nanoparticle	98
4.4.1	Micro X-ray diffraction technique	98
4.4.2	Dielectric Measurements:	107
4.4.3	Effect of different gold concentration on the CDW state .	113
4.5	Conclusion	116
5	Dielectric properties of CDW state in polypyrrole nanotube	119
5.1	Introduction	119
5.2	Dynamics of CDW state	120
5.3	DC resistivity and Low Frequency impedance measurement . .	126
5.3.1	Results	127
5.3.2	Discussions & Conclusions	135
6	Metallic behavior in Polypyrrole nanowire	137
6.1	Experimental	139
6.2	Results	140
6.2.1	Resistivity measurements	140
6.2.2	Magnetoresistance (MR)	142
6.3	Discussions	143
6.4	Conclusion	147

7 Summary and Outlook

149

List of Figures

1.1	Peirls instability	8
1.2	Conjugated polymer	17
1.3	Soliton	20
1.4	soliton kink	21
1.5	Soliton band structure	22
1.6	Polarons and bi-polarons	23
2.1	Schematic	29
2.2	Reaction of Chloroauric acid and pyrrole	31
2.3	Schematic of SEM	33
2.4	SEM picture of gold-ppy composite nanotube	34
2.5	Schematic of TEM	35
2.6	TEM picture of composite nanotubes where gold not visible	36
2.7	TEM picture of composite nanotube gold visible	37
2.8	SIMS of composite nanotube	38
2.9	Thermal evaporator	42
2.10	contacted single nanowire	47
2.11	Bigger electron sputtering	48
2.12	Schematic for marker and smaller electrode fabrication	49
2.13	image of the substrate after marker and electrode fabrication	50
2.14	Schematic for connecting single nanotube	51

2.15	contacted single nanowire	53
2.16	contacted single nanowire	54
2.17	Insert design	55
2.18	IV-check for Giga-ohm	57
2.19	<i>Low noise magnetoresistance measurement</i>	58
3.1	HAXPES C spectra of PPy	63
3.2	HAXPES C spectra of AuPPy	65
3.3	HAXPES N spectra	67
3.4	HAXPES gold spectra	68
3.5	VRH and activated plot of PPy and AuPPy	71
3.6	Magnetoresistance of PPy and AuPPy	73
3.7	Switching different zone of PPy and AuPPy	76
3.8	Gap Zone of PPy and AuPPy	78
3.9	Temperature variation gap zone of PPy and AuPPy	79
3.10	Power law dependence PPy	80
3.11	Power law dependence of AuPPy	81
3.12	Comparison of switching for 100 nm AuPPy and PPy	83
3.13	Temperature dependence of threshold voltage and hysteresis	84
3.14	SIMS after and before switching	87
3.15	Different switching process	88
4.1	Specially designed cell for X-ray micro-diffraction	100
4.2	Different configuration XRD of AuPPy in membrane	101
4.3	2D image and intensity variation of XRD spot	102
4.4	time evolution of gold peak for 400 nm and 80 nm AuPPy nanotube	103
4.5	x-ray diffraction and Williamson-Hall plot	105

4.6	x-ray diffraction and Williamson-Hall plot	106
4.7	Schematic for dielectric measurement connection	107
4.8	Wall thickness measurement of 200 nm and 50 nm composite nanotube.	108
4.9	Temperature dependence dielectric constant and loss of different diameter nanotube	111
4.10	Frequency dependence dielectric constant, conductivity and loss of 50 nm nanotube	112
4.11	Dependence of switching and dielectric constant for different wt% of gold	113
4.12	Different zone in IV of 50 nm AuPPy nanotube	115
5.1	Phase diagram of 100 nm PPy nanotubes	127
5.2	Conductance and Cole-Cole plot	129
5.3	Frequency dependence dielectric permittivity and loss at various temperature	130
5.4	activation energy of relaxation time and resistivity	130
5.5	Frequency dependent dielectric constant and loss at different bias	133
6.1	resistivity at different current bias	141
6.2	Longitudinal and transverse magneto-resistance	144
6.3	magnetoresistance below and above switching	144
6.4	Magnetoresistance at different bias	145
6.5	Phase diagram of polypyrrole nanowire	147